

MAPEFLEX PU 35 CR

Polyurethane sealant with high modulus of elasticity, resistant to chemicals, suitable for clean rooms and environments with food and beverages



WHERE TO USE

Sealing expansion and contraction joints on vertical and horizontal surfaces that come into accidental or prolonged contact with aggressive chemical liquids, including in those areas subject to the passage of light vehicles.

Sealing joints in sterile chambers in which an atmosphere with a low level of air pollution particles needs to be created and maintained.

Some application examples

- Production plants in general.
- Bottling plants and areas where liquids are handled, including moderately aggressive liquids.
- Storage warehouses.
- Safety tanks for industrial storage tanks.
- Water treatment plants.
- Foodstuffs industries.
- Pharmaceutical industries.
- Operating theatres.
- Cleanrooms in general.

TECHNICAL CHARACTERISTICS

Mapeflex PU 35 CR is a highly deformable, high modulus of elasticity, thixotropic sealant particularly resistant to chemicals and to a wide range of aggressive liquids in compliance with EN 14187-4, EN 14187-6 standards (see table 1) and ISO 2812-1.

To meet the high standards required for sealants approved for sterile chambers, **Mapeflex PU 35 CR** is certified as CSM (Cleanroom Suitable Material) by IPA Fraunhofer for its chemical and biological resistance and as a product with low emission of VOC, this latter feature is also certified by the GEV Institute.

Mapeflex PU 35 CR complies with the requirements of the HACCP plan (Hazard Analysis and Critical Control Points) for use in food processing environments.

Mapeflex PU 35 CR is also suitable for contact with drinking water, as certified by tests carried out according to MS 1583: Part 1: 2003 Guidelines (Test Report No: 2022CE1938, emitted 4 August 2022).

Mapeflex PU 35 CR sets progressively by reacting with the water vapour in the air or in the pores in the substrate to form elastic, deformable rubber that adheres to the substrate. Once set, it compensates for compressive,

tensile and torsional movements in joints while guaranteeing high resistance to punching and surface friction.

Mapeflex PU 35 CR is resistant to dry service temperatures of -30°C to +80°C.

Mapeflex PU 35 CR complies with European Standard EN 11600 class 25 HM (with **Mapei Primerseal M**), class 20 HM (without priming).

[Table 1](#)

Type of substance	Concentration %	Contact time			
Fresh water		72 hours	OK	28 days	OK
Seawater		72 hours	OK	28 days	OK
Diesel fuel		72 hours	OK*	28 days	OK*
Petrol		24 hours	NO		
Avgas		24 hours	NO		
Engine oil		72 hours	OK	28 days	OK
Brake fluid		72 hours	OK*	28 days	NO
Caustic soda	10	24 hours	OK	72 hours	OK*
Ethanol	15	24 hours	OK	72 hours	OK*
Acetic acid	10	24 hours	OK*	72 hours	OK*
Lactic acid	20	72 hours	NO		
Fruit juice		24 hours	OK		
Freshly-squeezed fruit juice		24 hours	OK		
Phosphoric acid	10	24 hours	OK	72 hours	OK*
Ammonia		24 hours	OK*	72 hours	OK*
Oleic acid		24 hours	OK*	72 hours	OK*
Sulphuric acid	25	72 hours	OK	7 days	NO
Xylene		24 h	NO		
MEK		24 h	NO		

OK = suitable for contact

OK* = suitable for contact but the original characteristics of sealant may be slightly affected

NO = not suitable for contact

RECOMMENDATIONS

- Do not apply on damp or wet surfaces.

- Do not apply on bituminous surfaces potentially affected by oil bleeding.
- Do not apply if the temperature is lower than +5°C or if the level of humidity is lower than 40%.
- At low temperatures, we recommend warming the sealant by standing it in warm water or rubbing the cartridge vigorously before use so it is easier to extrude and smooth over.

APPLICATION PROCEDURE

Mapeflex PU 35 CR is supplied ready-to-use in 600 ml soft cartridges wrapped in aluminium and it is applied using a conventional manual, electric or pneumatic silicone gun for 600 ml soft cartridges.

Application of the product

All the surfaces to be sealed must be dry, sound and free of all traces of dust, loose portions, cement laitance, oil, grease, wax, old sealant and paint, rust, form-release compound and anti-evaporation products.

When applying the sealant, the joint must be at least five times the maximum permitted design movement of the joint so that the sealant can absorb any movement in the joint correctly (e.g. if the design movement is 5 mm, the joint must be at least 25 mm wide).

To set the depth of **Mapeflex PU 35 CR** and prevent it from adhering to the bottom of the joint, insert **Mapefoam** compressible, expanded foam cord along the bottom of the joint. The diameter of the cord should be 10-20% greater than the maximum width of the joint to be sealed.

Set the depth of the sealant according to the width of the joint to be sealed as indicated in table 2:

[Table 2](#)

Width of joint	Depth of sealant
up to 10 mm	same as width
from 11 to 20 mm	10 mm in all cases
more than 20mm	half the width

Brush-apply **Mapei Primerseal M** along the edges of the joint where the sealant must adhere and leave it to dry (3-4 hours, depending on the surrounding temperature and absorbency of the substrate); the primer must be dry to the touch before applying **Mapeflex PU 35 CR**.

Fill the joint with **Mapeflex PU 35 CR** using a silicone gun from the **Mapei Gun** range, depending on site requirements (contact Mapei Head Office for further details).

Place masking tape along the edges of the joint for a perfect finish.

Extrude the sealant into the joint without entraining air.

Remove any excess sealant from the edges of the joint and smooth the surface with soapy water for a flat and uniform surface.

If masking tape has been placed along the edges of the joint, it must be removed while the sealant is still fresh.

CONSUMPTION

The density of **Mapeflex PU 35 CR** is 1.42 g/cm³.

Approximate consumption rates for various sizes of joints are indicated in table 3.

[Table 3](#)

Width of joint (mm)	5	10	15	20	25	30	35	40
Depth of sealant (mm)	5	10	10	10	12.5	15	15	15
Ø Mapefoam (mm)	6	15	20	25	30	40	40	2 x 25
Metres of sealant per 600 ml soft cartridge	24	6	4	3	1.9	1.5	1.1	1
Consumption of Mapei Primerseal M (g)	5	15	15	15	25	30	30	30

CLEANING

Remove **Mapeflex PU 35 CR** from surfaces, tools, clothing etc. with alcohol, nitro thinners or turpentine before it sets. Once set it must be removed mechanically or with **Pulicol 2000**.

PACKAGING

Mapeflex PU 35 CR is supplied in boxes of twenty 600 ml soft cartridges.

COLOURS

Mapeflex PU 35 CR is available in 113 grey.

STORAGE

12 months in its original, sealed packaging at a temperature of +5°C to +25°C.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Instructions for the safe use of our products can be found on the latest version of the Safety Data Sheet, available from our website www.mapei.com.

PRODUCT FOR PROFESSIONAL USE.

TECHNICAL DATA (typical values)

PRODUCT IDENTITY

Colour:	113 grey
Consistency:	smooth thixotropic paste
Density:	1.42 g/cm ³
Brookfield viscosity:	1,200,000 mPa·s (Helipath spindle f – 5 rpm)
Dry solids content:	100%
EMICODE:	EC1 Plus - very low emission

APPLICATION DATA (at +23°C - 50% R.H.)

Application temperature range:	+5°C to +35°C
Time to form surface skin:	1 h and 30 min
Final hardening time:	3.5 mm/24 h 5.0 mm/48 h 8.5 mm/7 days

FINAL PERFORMANCE

IPA Fraunhofer CSM report MA 1510-788:	chemical resistance: good
--	------------------------------

IPA Fraunhofer CSM report MA 1510-788:	outgassing VOC (+23°C/+90°C): ISO-ACC class -7.3
IPA Fraunhofer CSM report MA 1703-896:	biological resistance: good
Shore A hardness (DIN 53505):	36
Tensile strength (ISO 37 TYPE 3):	3.5 N/mm ²
Elongation at failure (ISO 37 TYPE 3):	700%
Modulus at 100% (ISO 37 TYPE 3):	0.8 N/mm ²
Elongation in service (ISO 11600):	25% (with Mapei Primerseal M) 20% (without priming)
Tear strength (ISO 34-1):	18 N/mm
Elastic recovery (ISO 7389):	95%

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.com.

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

Mapei S.p.A.

Via Cafiero, 22, 20158, Milano



+39-02-376731



www.mapei.com



mapei@mapei.it

446-7-2025 en (IT)

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

